

GriP AntiSlip Spray-Remover

Technical Data Sheet and user guide

GriP Safety Coatings AG
Industriestrasse 13
CH-6343 Rotkreuz

Tel +41 (0)41 726 20 80
Fax +41 (0)41 726 20 81

info@grip-antislip.com
www.grip-antislip.com

GriP AntiSlip is the only anti-slip coating which can be easily removed using the specially developed GriP AntiSlip Spray-Remover. GriP AntiSlip Spray-Remover can remove max. 2 square meters of coating. The surface will not be affected.

Instructions

Please make sure to wear protective gloves

Please shake the Spray can thoroughly before usage.

Keep about 10cm distance to the surface when applying the remover and apply a film over the complete coated surface. Removing process takes at least 15 minutes and can vary depending on temperature and air humidity. Please use the below pictures for guidance. When the coating has been "lifted" from the surface, use a plastic putty knife to remove the coating.

In case some coating remains on the surface, please use the Spray Remover again and repeat the removing process.

Rinse the surface thoroughly with water after the removing process.



After 15 minutes reaction time

Environment

Biologically degradable >93% after 28 days conform OECD Test 302B (Attest-Nr. 09101902H)

Technical Information

Basis:

Solvent mixture, Tensides, Additives

Viscosity: fluid

Density: 92 g/ml

Flash point: 27°C

HS-Code: 3208-1010